

TECHNICAL DATA

TYPICAL APPLICATIONS

- > Designed for today's high tech transportation industry
- > Metal preparation, painting and coating
- > Removes cleanly with no adhesive residue in application temperatures to 200 °F
- > Strong backing to hold up to the most demanding applications

ADVANTAGES AND BENEFITS

- > No adhesive residue
- > Engineered holding power
- > Strong backing for tear and sliver resistance
- > Excellent adhesion to metals, rubber and plastics
- > Conformability for rounding curves and contours
- > Clean flat edge's for sharp paint lines
- > Solvent and moisture resistant to minimize bleed-through

CONSTRUCTION

Overall Grade/Function: Performance Grade

Backing: Smooth crepe paper

Adhesive: High performance, rubber adhesive

COLOR(S)



Natural (NAT)

STANDARD WIDTHS

18mm 24mm 36mm 48mm

STANDARD LENGTHS

55 m

Contact your Shurtape sales representative for other available sizes



PHYSICAL PROPERTIES

	STANDARD	METRIC
Tensile Strength	28 lbs/in width	49.0 N/10mm
Adhesion to Stainless Steel	34 oz/in width	3.72 N/10mm
Thickness	6.6 mils	0.17 mm
Elongation	10 %	10 %
Service Temperature Range	200 F	93 C

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC. Quality Assurance and Technical Service Departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

APPLICABLE SPECIFICATIONS

ASTM D6123/D6123M-97

STORAGE & USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

"Shurtape" is a registered trademark of Shurtape Technologies, LLC

Form# TDS- CP 450 - 03/27/2007